

DESCRIPTION

Water borne acrylic gypsum.

PRINCIPLES CHARACTERISTICS

- Good adhesion .
- Easy application and workability.
- Suitable for internal and external application.
- Excellent weathering resistance.
- Excellent resistance to color retention.
- High durability.
- High build film.

BASIC DATA AT 25°C**Mass density**

1.78 g/cm³

Recommended dry film

140 micron / coat

Theoretical spreading rate

0.5 – 0.75Kg/ m²

Touch dry after

1 hr. depending on the temperature & humidity

Overcoating interval

12 hours at 25°C

Flash point

above 65°C

Viscosity

220 poises

Solid content

75 %

Hard Dry

5 hrs

Storage Temperature

10-35°C

Shelf life(cool & dry place)

At least 12 months

Colors and Gloss

White-Flat

Full cure

24 hours

RECOMMENDED SUBSTRAT CONDITION AND TEMPERATURES

- Previous mortared cementitious walls.
- Substrate temperature should be at least 10 °C .

CLEAN-UP

Clean hands and tools immediatly
With tap water.
Clean spills right away with a damp cloth.

DIRECTION FOR USE

INSTRUCTION

- Applying by suitable blande or spatula.
- The temperature of the paint should preferably be above 15°C, otherwise Extra tap water may be required to obtain application viscosity.
- Must be protected from freezing at all times during storage .

APPLICATION

CLEANING SOLVENT

Tap water

SAFETY AND HEALTH

In case of eye contact treat any foreign body by flushing with large amounts of water .
For skin contact repeated exposure may cause skin dryness or cracking ;also it may cause allergic reaction.
For safety when applying it is advisable to wear hand gloves.
Keep out of the reach of children , do not use or store by hanging on a hook.
Lead to toxic exposure that cause serious damage for brain especialy for children and pregnant women.

SHIPPING

Packing

5 L-17 L

Storage Condition

Store away from extreme temperature.
Containers should be kept closed during storage.

Limitations

This is a water base paint although care should be taken.

TDS-BMA-B3-C-12

