

## **BMA ELASTIC PUTTY**

Code: 1BM-EPS120

Color: White

### **PROPERTIES**

BMA Elastic Putty is a water-based styrene acrylic modified roof coating with a sanding finish, formulated to act as a supreme isolation for several types of roofing substrates. It is able to provide a long lasting protection from ultraviolet radiation, dirt adherence to the surface, ozone, rain and snow effect. With its elastomeric property, Elastic Putty is able to stretch and return to its original shape without losing any of the protection properties. BMA Elastic Putty is applied on walls, ceilings, concrete floors.

### **RECOMMENDED USES**

BMA Elastic Putty could be used for:

- ✓ Concrete and build-up roofing
- ✓ Asphalt membranes
- ✓ Under tiles in kitchens, bathrooms, were humidity is high
- ✓ As a water-proofing and heat-reflective coating on roofs
- ✓ As a water-proofing primer under outdoor textured coatings

### PERFORMANCE BENEFITS

- ✓ Waterproofing and weatherproofing properties
- ✓ UV protection and solar reflectivity leading to an anti-aging characteristic
- ✓ Resistance to dirt fungi, and algae grow up
- ✓ A long lasting roof isolation
- ✓ Cooling cost savings by reduction of temperature extremes found on roofs
- ✓ Minimizing the slippage on horizontal surfaces due to the sanding finish

Fax: +961 1 885685



#### CHARACTERISTIC PHYSICO-CHEMICAL DATA

Tests	Norms	Results
Total solids, by weight	ASTM D2369	60.38 %
Consistency, at 25°C	ASTM D562	40 Poises
Specific Gravity (g/cm3)	ASTM D1475	1.322
Total Volatile Organic Compound (VOC)	ASTM D3960	32.2 g/L
Spreading Rate at 250 µm DFT (1)	-	2 m²/L
Recommended WFT (2) at 5% Dilution	-	536 µm

<sup>1)</sup> DFT: Dry Film Thickness 2) WFT: Wet Film Thickness

### **APPLICATIONS GUIDE**

### **Surface Preparation**

Before applying BMA Elastic Putty, all necessary pretreatment must be done. Surface should be clean, dry and free of all contaminants (oils, dust, dirt, etc...) in order to avoid the risk of surface failing.

#### **Concrete surfaces:**

Concrete substrate must be well prepared in order to avoid any coating defects.

For new surface, ensure that concrete is completely cured for at least 30 days.

For both fresh and old concrete, decontamination is required to remove any dust, oil, grease, laitance, fatty acids or any additional contaminants. Acid etching is recommended using Eksen Kimya Hydrochloric Acid Solution. Decontamination could be also done using detergent scrubbing, low pressure water cleaning, or steam.

After cleaning, fill and repair any surface irregularities (cracks, holes and pores) with the cementitious mixture fortified with BMA SBR.

Allow concrete substrate to dry then check the moisture and the pH of the substrate. Ensure that the pH is between 6 and 9 since alkalinity can affect and destroy paint adhesion. For the moisture content, make sure that it does not exceed 4% (by weight). Otherwise, the concrete surface is not a good candidate for painting.

2 | 4

Nahr El Mot, Industrial Valley – Lebanon Tel.: +961 1 885385/485 Fax: +961 1 885685

E-mail: customerservice@bmapaints.com



## Thinning

Apply the first layer of Elastic Putty with a brush or a roller after dilution with 80 to 100% of tap water and the second layer after dilution with 40 to 50% of tap water and the third layer form 0 to 20% of tap water.

## Application

BMA Elastic Putty should be applied in a well ventilated area where the humidity does not exceed 75% and the temperature is between 10°C to 35°C.

Follow the below recommended system to provide a maximum protection to the substrate after a well cleaning, drying and removal of contaminations and dust residues:

- Apply the first layer of Elastic Putty, let it dry for 6-8 hours then continue with the second layer.
- Let dry for 6-8 hours and finalize with the third layer of BMA Elastic Putty.
- Let the system dry for 12 hours then if necessary finalize with a BMA Water Based Paint.

## **Drying Time**

Surface (touch) dry: 2 hours

Through dry: 4 hours Dry to over coat: 6-8 days

### **AVAILABLE PACKAGING**

1 US Gallon = 3.786 L; Pail = 17 L

### STORAGE CONDITIONS & SHELF LIFE

BMA Elastic Putty should be stored in undamaged and unopened containers in a well ventilated area where temperature varies between 5°C and 35°C. The product must be kept away from any heat or freezing source.

Under these storage conditions, the shelf life of BMA Elastic Putty will be 1 year. After this period, its quality will be subjected to re-inspection. Proper handling is essential to maintain good quality.

Fax: +961 1 885685

E-mail: customerservice@bmapaints.com



#### **HEALTH & SAFETY**

Before using this product please consult our Safety Data Sheet (SDS) for complete information on Hazards Identification, First-Aid and Fire-Fighting Measures, Accidental Release Measures, Handling and Storage, Exposure Control and Personal Protection, Stability and Reactivity, Toxicological Information, and Transport Information.

## **QUALITY ASSURANCE**

BMA Commercial & Industrial s.a.l is a holder of the ISO 9001:2015 and ISO 45001:2018 certificates, which guarantees that all operations are conducted in compliance with International Standards.

#### TDS.249- Edition #: 1

IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, BMA Commercial & Industrial s.a.l expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.

Fax: +961 1 885685